



TOP SECRET COATINGS

1999 Elizabeth St. No. Brunswick, NJ 08902

Phone: 732-821-3200 Fax: 732-821-8180

info@topsecretcoatings.com

www.topsecretcoatings.com

TS-780 Mono-Epoxy Primer

Single Stage Epoxy Primer

Mono-Epoxy Primer is a new generation single stage epoxy primer that is oxygen cured eliminating the need for mixing multiple components together and the hassle and complications of limited pot life that go along with it. Ease of use makes it a compelling choice when compared to two component epoxy primers.

Mono-Epoxy Primer is all about getting the job done quickly, easily and effectively. Even better; it produces a nontoxic film making it friendly to you and the environment. It is a true barrier to water, vapors and gasses. Corrosion control and weather-ability are excellent. It builds well with-out sagging or running. It self levels to a smooth finish without leaving behind dimples, orange peel or bubbles. It is submersible long term which says a lot about versatility and quality.

Adhesion, film build, hide, coverage, hardness, scuff and impact resistance are all excellent. It resists the damaging effects water, of harsh chemicals, spilled fuel, antifreeze, brake fluid, trans-mission fluid and staining agents. Corrosion control and weather-ability are superior to most al-kyd primers. It successfully resists hot tire pick up when applied to concrete floors and it is com-patible with a wide variety of top coating systems.

Stats: Covers 250-300 square feet per gallon on porous surfaces such as concrete. Dry to the touch in 2-4 hours. Pot life: Not applicable. High in solid content so it will require dilution in spray applications. Recommended thinner; TS-605 Thinner; or TS-101 Thinner, do not substitute. Available in one gallon and five gallon containers. Finish is low sheen. Not lacquer-proof. Not recommended for use with hot-solvent top coating systems. Adhere to Application Instructions Sheet included with order, label directions and standard industry application practices.

Product Features:

- Eliminates the need for mixing multiple components
- A fully submersible barrier to water, vapors and gasses.
- Acceptable for interior and exterior applications.
- Will not pick up due to hot tires.
- Self leveling formula reduces brush and roller marks.
- Allows for low temperature applications down to 40F.
- Lead free nontoxic safe to use formula.
- Provides good resistance to chemicals.

PERFORMANCE DATA SHEET

TS-780 Mono Epoxy Primer

COLOR(S): White and Red Oxide

PRODUCT TYPE: Epoxy-Ester Primer

DESCRIPTION: A single component alkyd-epoxy primer recommended for use on a wide variety of surfaces including structural steel, concrete floors, masonry, fiberglass, and floors. Acceptable for use as a corrosion control primer and base coat. It provides good adhesion, film build, hardness and cover-ability over a variety of surfaces. It offers excellent abrasion, scuff and mar resistance as well as a barrier to water, water vapor, and gases. Withstands long term im-mersion and extreme weather conditions.

Intended Use: For use as an epoxy primer coat

PHYSICAL CHARACTERISTICS

VISCOSITY: N/A

DRY TO TOUCH: 30 minutes

TACK FREE: 1 hour

TIME TO RECOAT: 1 hour

DRY HARD: 1-2 hours

WEIGHT SOLIDS: 68-70%

VOLUME SOLIDS: N/A

WEIGHT PER GALLON: N/A

V.O.C. : 550 grams per liter

FLASH POINT: 105° F

PRACTICAL COVERAGE: 250-300 square feet when applied at 4 mils wet film thickness per gallon depending upon surface to be coated.

SURFACE PREPARATION: Scuff, sand, grind, or blast all surfaces as needed. Surface to be primed must be free of all dirt, grease and foreign material and properly prepared. Concrete, tile and masonry: Should be etched with TS-695 Etching Cleaner according to label directions. Metals: Clean with TS-695 Etching Cleaner.

APPLICATION: Can be brushed, rolled, or sprayed on

THINNING: Thin when necessary with TS-605 Thinner

CLEAN-UP: Tools and equipment may be cleaned with TS-605 Thinner