

ANTIFOULING COMPATIBILITY CHART

		EXISTING BOTTOM PAINT				
		HARD ANTIFOULING	DURABLE ABLATIVE	SOFT ABLATIVE	MODIFIED ANTIFOULING	FRESHWATER ANTIFOULING
		Baltoplate Black Widow® Bottomkote Aqua Bottom Pro Gold! Bottom Shield Defense Vivid® Epoxy Cop Sharkskin Talon Trinidad® (All) Tropikote Ultra Ultra-Kote Unepoxy (All) VC Offshore	Cukote Hydrocoat® (All) Horizons Micron CSC Micron Extra Micron Optima Neptune 5 PCA Gold! Trilux 33 Ultima SR-40 Ultima SR-60	Ablative Plus AF-33 ACT Aqua-One Bottomkote NT CPP Micron CF Micron Optima Micron WA Monterey Pacifica Plus Proguard Ablative Smart Solution Super B Ablative Ultima Eco Armor	Biocop TF* Bottomkote Pro Micron 99* Micron 66* Seamate Ultima SSA Islands 44 TF* Tropikote EX* Islands 44 Plus* Biotin Plus *	FW 21 VC 17 SR 21 VMG
NEW BOTTOM PAINT	Black Widow® Trinidad® SR Trinidad® Pro Trinidad® HD Vivid®	Sand and Apply	Heavy Sand and Apply	Remove	Remove	Remove
	ECO HRT® Premium HRT® Unepoxy HRT®	Sand and Apply	Light Sand and Apply	Light Sand and Apply	Sand and Apply	Remove
	Odyssey® HD Ultima SR-40™ Ultima SR-60™ Odyssey® Triton	Sand and Apply	Light Sand and Apply	Sand and Apply	Heavy Sand and Apply	Remove
	Hydrocoat® Hydrocoat® Eco Neptune HRT®	Light Sand and Apply	Power wash and Apply	Light Sand and Apply	Sand and Apply	Sand and Apply
	SR 21™	Sand and Apply	Remove	Remove	Remove	Clean and Apply

Bottomkote NT™, Aqua™, ACT™, Micron CSC™, Micron Optima™, Micron Extra™, Micron WA™, Proguard Ablative™, Micron 99™, Micron 66™, VC-17™, Baltoplate™, Epoxy Cop™, Ultra™, VC Offshore™ and Pacifica Plus™ refer to products sold by Interlux®. Armor™ refers to a product sold by Flexdel. Sharkskin™, Talon™, Tropikote™, Cukote™, Biocop TF™, Islands 44 TF™, Tropikote EX™, Islands 44 Plus™, Biotin Plus™, Monterey™, Smart Solution™, VMG and AF33™ refer to products sold by New Nautical Coatings.

*Tin copolymer paints and modified antifouling paints (SPC technology) should be sealed with a coat of 6627 Tie Coat Primer, allow to dry 4 hours and apply new antifouling paint. This document is intended as a guide only, additional preparation may be involved due to condition and age of substrate.