

BLUE WATER[®]

MARINE PAINT

MEGA GLOSS[™]

The New Science of Polyurethane Finishes[™]

POLYURETHANE TOPSIDE ENAMEL

- Super High Gloss
- Smooth Finish
- Excellent Handle & Flow
- Superior UV Protection Prevents Fading
- Resistance to Tough Chemicals
- Fiberglass, Steel, Aluminum, Wood
- Excellent Recoatability
- Tremendous Coverage & Hiding



MEGA GLOSS - THE NEW SCIENCE OF POLYURETHANE FINISHES[™] - POLYURETHANE TOPSIDE ENAMEL

MEGA GLOSS[™] is a technically advanced, single component topside polyurethane enamel giving you a hard protective coating for super high gloss, color retention, and long durability. MEGA GLOSS is fast drying which when brushed or rolled gives a smooth finish with excellent handle and flow. This widely used topside polyurethane enamel has tremendous resistance to tough chemicals, cleaning solutions and ultraviolet light with its advanced ultraviolet technology. Can be used on fiberglass, wood, aluminum and steel. It's like wrapping your boat in glass!

SUGGESTED USES: Topside, Decks, Cabin, Masts, Bilge, Waterline, Boottop Striping

LIMITATIONS: Do not apply if material, substrate or ambient temperature is below 50°F or above 95°F.

COLORS: Available in over 30 factory packaged colors, as well as 1000 mixed colors.

FINISH: Gloss

VEHICLE TYPE: Polyurethane Alkyd Resin

SOLVENT TYPE: High Flash Naphtha

VOC: 3.76 lbs. / gal (450 grams / liter)

SOLIDS BY WEIGHT: 50%

WEIGHT PER GALLON: 10 lbs. per gallon (varies by color)

RECOMMENDED DRY FILM: 4.0 mils

COVERAGE: Theoretical coverage at two mils dry is 400 square feet per gallon, and recommended thickness of 4 mils dry would require 2 full coats. Material losses during mixing and application will vary and must be taken into consideration. Expect 50% less coverage on bare, rough or sandblasted surfaces.

VISCOSITY AT 75°F (24°C): 70-80 KU

AVERAGE DRY TIME 75°F: Dries to touch in 4 hours. Lower temperatures & higher humidity will slow down dry times.

RECOMMENDED REDUCER: Xylene for spray application, Hi Flash Naphtha for brushing or rolling

RESISTANCE TO: Chemical Resistance, Abrasion, Oils, Grease, Rust, Corrosion, Mildew, Chipping and Fading

RECOMMENDED PRIMERS: Mega Gloss Primers 8735 White, 8736 Black, 8737 Red, 8738 Gray.

APPLICATION: Brush, Spray or Roller

Roll: 1/2" nap mohair metal, lambskin, phenolic core roller. Keep roller wet. Roll in one direction, rewet, then cross roll. Product can be reduced as needed with Hi Flash Naphtha to allow proper flow out and performance.

Spray: Conventional Air Gravity Feed 59-70 psi, Tip Size .055 - .070, Airless 2200-2500 psi, Tip Size .013-.017. Product can be reduced with Xylene as needed for proper flow out and performance. For Air Spray reduce 25% with enamel reducer (Xylene.).

SURFACE PREPARATION: Water blast surface to remove all loose paint, dirt, oils and grease. Abrade with 240 grit dry sandpaper or equivalent. Solvent wipe down to remove all sanding residue. Prime with Mega Gloss Primer for best results.

POT LIFE: Not Applicable

SHELF LIFE: Maximum 12 months

MIXING: Mechanically mix for 10 minutes, making sure that all solid material is mixed thoroughly.

PACKAGE: 1 Gallon cans, 5 gallon pails.

CLEANUP: Xylene for Equipment.

ACTIVE INGREDIENTS:

Alkyd Resin	066070-60-8
Polyurethane Resin	Proprietary
Titanium Dioxide	13463-67-7
Talc	14807-96-6
Calcium Carbonate	1317-65-3
Aromatic Hydrocarbons	64742-95-6

BLUE WATER MARINE PAINT

1999 ELIZABETH STREET, NORTH BRUNSWICK, N.J. 08902
(800) 628-8422

www.bluewatermarinepaint.com

This product contains a maximum of 3.76 pounds of VOC per coating. Maximum VOC content 450 grams/liter.